



安徽艾约塔硅油有限公司

Iota Silicone Oil(Anhui) Co., Ltd

安徽省蚌埠市高新区兴中路 985 号日月科技园

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

电话: 86-552-3827158

Tel: 86-552-3827158

传真: 86-552-3822922

Fax: 86-552-3822922

Silicone Gel IOTA 6250LC

IOTA 6250LC is a two-component silicone gel, mainly used for

- Automotive electronic precision electrical circuits and hybrid circuits, solar cell modules
- Sensors, high-power rectifiers, rectifier bridges, intelligent water meters
- Sealing of electronic components, circuit boards, modules, etc. of optoelectronic equipment

Product features

- Medium viscosity, transparent, two component
- Room temperature curing or heating curing
- After curing, there are no by-products, with characteristics such as low hardness, low shrinkage rate, and no small molecule silicone oil precipitation
- Wide resistance to high and low temperatures, good damping performance, and weather aging resistance
- Capable of reliably protecting sensitive microelectronic components from moisture and corrosion

Product parameters

Inspection items	Component	Test Method	Results
Before curing			
Viscosity (mpa.s)	A	GB/T 2794	450~650
	B	GB/T 2794	900~1100
Density (g/cm ³)	A	GB/T 13354	0.97
	B	GB/T 13354	0.97
Mixing ratio	A:B	/	1:1
Mixed density(g/cm ³)	A+B	GB/T 13354	0.97
Operable time/25°C(h)	A+B	GB/T 7123	1
Gel time/25°C(h)	A+B	/	6
Curing conditions(°C×min)	A+B	/	120×30

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.siliconeoil.net



安徽艾约塔硅油有限公司

Iota Silicone Oil(Anhui) Co., Ltd

安徽省蚌埠市高新区兴中路 985 号日月科技园

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

电话: 86-552-3827158

Tel: 86-552-3827158

传真: 86-552-3822922

Fax: 86-552-3822922

After curing			
Density/25°C(g/cm ³)		GB/T 13354	0.97
Penetration(mm/10)		GB 269-85	250~450
Dielectric constant		GB/T1693	2.7
Volume resistivity(Ω·cm)		GB/T 1692	1015
Dielectric strength (KV/mm)		GB/T 1695	15
Refractive index/23°C		ABBE	1.405
Transmittance(%)		UV-VIS	>96
Flame retardancy		UL	94HB

The data in the table is for reference only, please refer to the measured data

Operation and Safety

- Before use, mix components A and B in a ratio of 1:1. Stirring time 5min. It is recommended to use after degassing for 5-10 minutes under -0.09MPa~-0.08MPa vacuum.
- The mixed rubber should be sealed and stored and used up within the safe operation period, otherwise it will slowly solidify and cause waste.
- This product is non-hazardous, but do not put it in the mouth or eyes. If it is accidentally splashed, rinse with plenty of water.
- Do not contact N, P, S, ion compounds such as sulfur, polysulfide compounds, polysulfone or other sulfur-containing materials, amines, polyurethanes, amides and azides, organotin compounds and silicone rubber containing organotin catalysts to avoid poisoning the platinum catalyst and failure to cure.
- Temperature and curing time: 25°C, 120min, no flow; fully cured at 120°C for 30min.
- The curing speed of the rubber has a certain relationship with the temperature. The curing will be slower at low temperatures.
- Both components A and B of the colloid must be kept sealed, be careful of leakage during transportation!

Package

- A / B Component 20KG
- A / B Component 200KG

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.siliconeoil.net



TECHNOLOGY MAKES LIFE BETTER

安徽省蚌埠市高新区兴中路 985 号日月科技园

电话: 86-552-3827158

传真: 86-552-3822922

安徽艾约塔硅油有限公司

Iota Silicone Oil(Anhui) Co., Ltd

Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158

Fax: 86-552-3822922

Storage and Shelf life

- Store in a dry place for a storage period of 12 months. If it expires, it needs to be retested and can be reused after passing the inspection.
- This type of product belongs to non hazardous goods and can be transported as general chemicals.

ADD: Sunmoon industry park, 985 Xingzhong Road, Bengbu, China 233000

Tel: 86-552-3827158; Fax: 86-552-3822922 Website: www.siliconeoil.net